

Gym Floor RFP - Addendum A

Since publishing the RFP, we have recently discovered that there is asbestos in the original tiles and the mastic used to adhere the glue to the surface when it was originally installed. Please include the cost of abatement in the bid separately from the flooring costs. If you have a floating floor option so the removal / abatement can be avoided, please include a bid for that too. The lab results are attached.

SEEML Reference Number:

210902023-PLM

Date Issued: 09/02/21



Southeast Environmental Microbiology Laboratories

102 Edinburgh Court
Greenville, SC. 29607
Phone: (864) 233-3770
Fax: (864) 233-6589

Asbestos Analytical Report By: Polarized Light Microscopy

This report has been prepared for **Clean Environments Inc.** the information and data has been checked for thoroughness and accuracy. The results reported apply only to the materials as received. The documents(s) contained herein are confidential and privileged information intended for the exclusive use of the individual or entity named above. This report shall not be reproduced except in full without SEEML's approval.

Client Project Name: St Andrews

The Following report was prepared using this test method(s) contained within this document.

- PLM Bulk Asbestos Fiber Analysis: EPA 600/R-93/116
- PLM 400 Point Count (<0.25%) EPA 600/R-93/116
- PLM 1000 Point Count (<0.1%) EPA 600/R-93/116
- PLM Carb 435 Level A Reporting Limit (<0.25%)
- PLM Carb 435 Level B (Reporting limit <0.1%)
- PLM by EPA/600/R-93/116 with Milling Prep 400 Point Count
- PLM Vermiculite Initial Screening EPA 600R-93/116
- PLM Cincinnati Method 600/R-04/004 (Amphibole Only)
- PLM Vermiculite Method SOF-V 198.8 (Step 1 Chrysotile & Prep)
- PLM Vermiculite Method SOF-V 198.8 (Step 2 (Amphibole))

Thank you for choosing SEEML Labs. We strive to provide superior quality testing, analytical data and customer service. SEEML is accredited through the National Institute of Standards and Technology (NIST) National Voluntary Accreditation Program (NVLAP) for bulk asbestos analysis LAP # 201031-0) and licensed by the Texas Department of State Health Services (License Number: 300474). This report must not be used to claim product certification, approval, or endorsement by NVLAP, NIST, or any agency of the US government.



Southeast Environmental Microbiology Laboratories - Asbestos Division

102 Edinburgh Court Greenville, SC 29607
 Phone: 864-233-3770, Fax: 864-233-6589 , www.seeml.com
 NVLAP Lab ID:201031-0 Texas Lic: 300474

PLM Asbestos Bulk Sample Summary

Client: Southern Flooring Charlie Dixon		Date Sampled: 08/31/21		
		Date Received: 09/02/21		
		Date Analyzed: 09/02/21		
		Date Reported: 09/02/21		
		Date Revised:		
		Project Name: St Andrews		
		Project No: 21215		
Analyzed by: Vrishni Sandoval	Project Address: 1095 Playground Rd			
	City, State. ZIP: Charleston, SC 29407			
Methodology: EPA/600/R-93/116 Without Gravimetry	SEEML Ref#:	210902023-PLM		
Lab No.:	% Asbestos Type	% Fibrous Non-Asbestos Material Type	% Non-Fibrous Material	Description/Location
Client No.:				
132A	None Detected	None Detected	100% Organic Matrix	Brown Mastic on top Gray Floor Tile/Gym
1				
132B	None Detected	None Detected	100% Organic Matrix	Gray Floor Tile/Gym
1				
132C	None Detected	None Detected	100% Organic Matrix	Black Mastic on back Gray Floor Tile/Gym
1				
132D	3% Chrysotile	None Detected	97% Organic Matrix	Beige Floor Tile/Gym
1				
132E	5% Chrysotile	None Detected	95% Organci Matrix	Black Mastic on back Beige Floor Tile/Gym
1				

Approved By: Jayson Dunn

Disclaimer:

The results in this report only apply to the samples as received.
 NOB samples are tested as a preliminary analysis. We highly recommend for Negative NOB samples resulting in less than 1% Asbestos to be verified by TEM or Point Analysis.

Inhomogeneous samples are separated into homogeneous subsamples and analyzed individually. NAD means no asbestos fibers were detected. When detected the minimum detection and reporting limit is less than 1% unless point counting is performed. Floor tile samples may contain large amounts of interference material and it is recommended that the sample be analyzed by gravimetric point count analysis to lower the detection limit and to aid in asbestos identification.

Guidelines for Interpretation:

Any opinions/interpretations expressed in this report are outside the scope of this laboratory's accreditation. Interpretation of the data and information within this document is left to the company, consultant, and/or persons who conducted the fieldwork. A material is considered regulated asbestos containing material (ACM) where the asbestos content is determined to be one percent or greater. Several organizations, including the American Conference of Government Industrial Hygienists (ACGIH); the American Industrial Hygiene Association (AIHA); the Indoor Air Quality Association (IAQA); the United States Environmental Protection Agency (USEPA); the Centers for Disease Control (CDC) as well as the California Department of Health Services (CADHS) have published guidelines for assessment and interpretation of analytical data indicating a tested material is ACM.